

Emission Test Certificate

Monday, 16th December 2019

Supplier: New Age Veneers Pty Ltd (14/22-24 Beaumont Rd, Mount Kuring-Gai, NSW, 2080,

Australia)

Sample Description: White Mountain Oak Panel

Date Tested: November 2019 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: ASTM D5116-2017 "Standard Guide for Small-Scale Environmental Chamber

Determinations of Organic Emissions from Indoor Material/Products".

Emission Data (7 days):

Green Building Council of Australia Green Star Design & As Built V1.2 - 13.1.2B & 13.2 Green Star Interiors V1.2 - 12.1.2B	White Mountain Oak Panel
Total Volatile Organic Compound Emission Rate Limit:	Total Volatile Organic Compound
≤0.500 mg/m²/hr	Emission Rate: 0.049mg/m²/hr
Formaldehyde Emission Rate Limit:	Formaldehyde Emission Rate:
≤0.1 mg/m²/hr	0.026 mg/m²/hr

Dr. Vyt Garnys

PhD, BSc (Hons) AIMM, ARACI, ISIAQ

ACA, AIRAH, FMA

Managing Director and Principal Consultant

Dale Duncan BSc (Hons)

Graduate Consultant

Tuan Duong

B.Eng. (Chemical)

Consultant

V1911058